

TECHNICAL DATA SHEET

MEBK44

| | |
|-----------------------------------|---------------------------|
| PRODUCT NAME | Black MB |
| RESIN SUITABILITY | LDPE, LLDPE, MDPE,HDPE,PP |
| LIGHT FASTNESS | 8.00 |
| MIGRATION | 5.00 |
| HEAT STABILITY (MAX. °C) | 300.00 |

Applications :

MEBK44 is 40% carbon black content masterbatch with an addition of filler designs for blown film, sheet extrusion and other applications. It exhibits good dilute ability together with optimum carbon black dispersion characteristics.

Method of Addition :

MEBK44 is designed for ease of dilution and homogeneous mixing and is therefore suitable for direct addition using automatic dosing units or by pre-blending.

Addition Rate :

The amount of masterbatch added depends on the performance requirements of the final application.

Packaging :

MEBK44 is supplied in regular pellet form packed in 25 kg. bag and 750 kg. bulk bag. It should be stored in a dry place.

Storage :

Recommended storage life up to 1 year provided it is stored as directed.

Regulatory Status :

Raw materials used in this product comply with:

- CONEG 94/62/EC
- Food Contact Materials EU NO. 10/2011
- Food Contact Resolution AP (89)1
- RoHS Directive 2015/863
- Toy Standard EN71 Part 3

This product can be used only for the application as specified here above. Customer should inspect the product in order to satisfy itself as to the suitability of the product for the customer's particular purpose.