

Specification
Minerene CAE152

Item	Specification	Method
Bulk density (g/cm ³)	1.21 ± 0.12	ASTM D 1895
Calcium carbonate content (%)	85 ± 2	ASTM D 5630 - 01
Color deviation (DE)	≤ 1.5	CIE Lab D 65
Density at 23°C (g/cm ³)	2.01 ± 0.20	ASTM D 1505
MFI 2.16 kg/190 °C (g/10min)	No flow	ASTM D 1238-04
Moisture content (%)	≤ 0.20	LA - W - 007

THE DATA ABOVE WAS OBTAINED FROM TESTS ON SAMPLES TAKEN DURING THE TIME OF PRODUCTION AND/OR PACKAGING OF THIS PRODUCT USING INTERNATIONAL STANDARD OR SALEE COLOUR TEST METHOD. WE DO NOT GUARANTEE THE SAME RESULTS WILL BE OBTAINED BY OTHERS IN THE OTHER LABORATORIES AND WE DISCLAIM LIABILITY RESULTING FROM THE USE OF THE CONTENTS OF THIS REPORT